



TECHNICAL DATA SHEET

CMC TYPE	65839
Supporting Base	Nomex® (Aramid) / Polyester (PET)
Colour	chamois
Thickness without adhesive in mm	0,090 ± 10 %
Thickness with adhesive in mm	0,140 ± 10 %
Adhesive Properties	
Kind of adhesive	Acrylic
Adhesive strength in N/10 mm	≥ 3,5
Thermal Properties	
Maximum temperature in °C	155
Short-time-temperature in °C	200
Flammability according IEC 60454-2	flame retardant
Isolation class VDE 0530	F
Electrical Properties	
Voltage testing	no breakdown
Breakdown voltage VDE 0303 in V_{eff}	5.500
Mechanical Properties	
Tensile strength in N/10 mm	70 ± 10 %
Elongation at break in %	≥ 10
Other Properties	
® Registered trade mark of Du Pont de Nemours	

Storage conditions: cool and dry (15 - 25°C, < 65% rel. humidity)

03/08

Quality guarantee: 12 months

The technical data are average values and subject to change without notice. They are not intended to replace user's testing.