



TECHNICAL DATA SHEET

CMC TYPE	70700
Product description	
Kapton® film with good thermal conductivity and very good insulating properties even at high temperatures. Easy and clean pre-assembly provided by the adhesive layer (also available in 0.025 mm film thickness on request).	
Substrate	Kapton® MT
Colour	brown
Thermal conductivity in W/(m·K)	0.46
Substrate thickness in mm	0.050 ± 15%
Total thickness in mm	0.078 ± 10%
Adhesive Properties	
Type of adhesive	acrylic
Adhesive strength according to internal method PV 1006-32 (180° peel from steel) in N/cm	≥ 2.0
Thermal Properties	
Temperature performance (max.) in °C	155
Flammability according to IEC 60454-2	flame retardant
Insulation class according to IEC 60085	F
Electrical Properties	
Breakdown voltage based on IEC 60243-1 in V _{eff.}	≥ 7'000
Mechanical Properties	
Tensile strength in N/cm	≥ 50
Elongation at break in %	≥ 20
Other Properties	
Liner	double-sided siliconized polyester film with the more repellent side covering the adhesive
* registered trade mark of DuPont de Nemours	
Information concerning regulation (EC) No 1907/2006 (REACH): This product contains one or more substances of very high concern (SVHCs) from the candidate list in amounts greater than 0.1% (w/w). Safe handling instructions can be found here: http://www.cmc.de/en/technical-information/reach.html	

Storage conditions: cool and dry (15 - 25°C, < 65% rel. humidity)

10/16

Quality guarantee: 12 months

The technical data are average values and subject to change without notice. They are not intended to replace user's testing.