



## TECHNICAL DATA SHEET

<b>CMC TYPE</b>	<b>10240</b>
<b>Supporting Base</b>	Polyester
Colour	colourless, yellow
Thickness without adhesive in mm	0,036 ± 10%
Thickness with adhesive in mm	0,070 ± 10%
<b>Adhesive Properties</b>	
Kind of adhesive	Acrylic
Adhesive strength in N/cm according to internal method PV 1006-32 (180° peel from steel)	≥ 3
<b>Thermal Properties</b>	
Temperature performance (max.) in °C	130
Short term temperature performance in °C (ca. 1 hour)	175
Flammability according IEC 60454-2	flame retardant
Isolation class according to IEC 60454-2	B
<b>Electrical Properties</b>	
Voltage testing	no breakdown
Breakdown voltage based on IEC 60243-1 in V <sub>eff.</sub>	7.500
<b>Mechanical Properties</b>	
Tensile strength in N/10 mm	≥ 60
Elongation at break in %	≥ 80
<b>Other Properties</b>	

Storage conditions: cool and dry (15 - 25°C, < 65% rel. humidity)

11/12

Quality guarantee: 12 months

The technical data are average values and subject to change without notice. They are not intended to replace user's testing.