Beschichten - Stanzen - Schneider

CMC Klebetechnik GmbH Rudolf-Diesel-Straße 4 Germany - 67227 Frankenthal 0049 (0)6233/872-300

TECHNICAL DATA SHEET

CMC TYPE	16101
Supporting Base	Laminate Polyester / Polyesterfleece
Colour	white
Thickness without adhesive in mm Weight without adhesive in g/m²	0,075 ± 10 % 70 ± 10 %
Thickness with adhesive in mm Weight with adhesive in g/m²	0,125 ± 10 % 120 ± 10 %
Adhesive Properties	
Kind of adhesive	Acrylic
Adhesive strength in N/10 mm	≥ 3,5
Thermal Properties	
Maximum temperature in °C	130
Short-time-temperature in °C	175
Isolation class VDE 0530	В
Electrical Properties	
Voltage testing	no breakdown
Breakdown voltage VDE 0303 in V _{eff.}	5.000
Electrolytic corrosion	AN 1,2
Mechanical Properties	
Tensile strength in N/10 mm	50
Elongation at break in %	30 - 50
Other Properties	

Storage conditions: cool and dry (15 - 25°C, < 65% rel. humidity)

Quality guarantee: 6 months

The technical data are average values and subject to change without notice. They are not intended to replace user's testing.

03/08