

CMC Klebetechnik GmbH Rudolf-Diesel-Straße 4 Germany - 67227 Frankenthal 0049 (0)6233/872-300

TECHNICAL DATA SHEET

СМС ТҮРЕ	18102 E93622 (M)
Supporting Base	Laminate impregnated crepe paper / Polyester
Colour	chamois
Thickness of laminate in mm Weight of laminate in g/m²	0,150 ± 10 % 130 ± 10 %
Total thickness in mm Total weight in g/m²	0,200 ± 10 % 180 ± 10 %
Adhesive Properties	
Kind of adhesive	Acrylic
Adhesive strength in N/10 mm	≥ 3,5
Thermal Properties	
Maximum temperature in °C	130
Short-time-temperature in °C	175
Isolation class VDE 0530	В
Electrical Properties	
Voltage testing	no breakdown
Breakdown voltage VDE 0303 in V _{eff.}	6.000
Electrolytic corrosion	AN 1,2
Mechanical Properties	
Tensile strength in N/10 mm	40 - 50
Elongation at break in %	45 - 60
Other Properties	

Storage conditions: cool and dry (15 - 25°C, < 65% rel. humidity)

03/08

Quality guarantee: 12 months

The technical data are average values and subject to change without notice. They are not intended to replace user's testing.