



Technical Data Sheet

CMC TYPE	70880, double-sided
Product description	
Kapton® film with good thermal conductivity and very good insulating properties even at high temperatures. Easy and clean pre-assembly provided by adhesive layers on both sides (also available in 0.025 mm film thickness on request).	
Substrate	Kapton® MT, thermally conductive
Colour	brown
Thermal conductivity in W/(m·K)	0.46
Substrate thickness in mm	0.050 ± 15%
Total thickness in mm	0.140 ± 10%
Adhesive Properties	
Type of adhesive	acrylic (both sides)
Adhesive strength in N/cm according to internal method PV 1006-32 (180° peel from steel)	≥ 2.5 (both sides)
Thermal Properties	
Temperature performance (max.) in °C	155
Insulation class according to IEC 60085	F
Electrical Properties	
Breakdown voltage based on IEC 60243-1 in V _{eff.}	≥ 7'000
Mechanical Properties	
Tensile strength in N/cm	≥ 50
Elongation at break in %	≥ 20
Other Properties	
Liner	siliconized paper
® registered trademark of DuPont de Nemours	

Storage conditions: cool and dry (15 - 25°C, < 65% rel. humidity)

03/18

Quality guarantee: 12 months

The technical data are average values and subject to change without notice. They are not intended to replace user's testing.