

# DuPont™ Kapton® FWR

## Polyimide Film

### Product Description

DuPont™ Kapton® FWR is a heat fusible polyimide-FEP fluoropolymer composite film that has a unique balance of excellent electrical, thermal durability, and chemical resistance properties. The properties of Kapton® FWR will provide a tough, high dielectric strength insulation with significantly improved hydrolysis resistance compared to other commonly used polyimide materials.

Kapton® FWR can be properly processed on most tape wrapping machines. It can be fused using either induction or radiant heat. Kapton® FWR films have a higher modulus and lower water vapor permeability than equivalent Kapton® FN films. The wire wrapping and sealing process may have to be modified to compensate for these differences.

Kapton® 150FWR019 film is constructed of a 1.0 mil Kapton® polyimide film with 0.5 mil of FEP fluoropolymer on one side. Kapton® 200FWR919 film is constructed of a 1.0 mil Kapton® polyimide film with 0.5 mil of FEP fluoropolymer on each side.

### Characteristics

- Excellent hydrolysis resistance
- UL 94 recognition: V-0
- High dielectric strength
- Mechanically Tough
- Heat Fusible

### Applications

- Magnet wire
- Traction motors: rail, auto, mining
- Industrial motor insulation
- Wind, hydro generators
- ESP motors
- High temperature
- High reliability
- Aerospace and specialty wires

# DuPont™ Kapton®

Polyimide Film

**Table 1. Typical Physical Properties of DuPont™ Kapton® FWR Polyimide Film**

Property	Unit	150FWR019	200FWR919	Test Method
Thickness	mil	1.5	2.0	ASTM D374
	µm	38	50	
Tensile Strength	kpsi	34	30	ASTM D882
	MPa	234	207	
Elongation	%	60	63	ASTM D882
Tensile Modulus	kpsi	520	430	ASTM D882
	GPa	3.6	3.0	
Dielectric Strength	V/mil	4500	5000	ASTM D149
	kV/mm	177	197	
Yield	ft <sup>2</sup> /lb	79.7	56.8	-
	m <sup>2</sup> /kg	16.3	11.6	
Density	g/cc	1.69	1.83	ASTM D1505
Dielectric Constant @ 1 kHz	-	2.7		ASTM D150
Dissipation Factor @ 1 kHz	-	0.0013		ASTM D150
Volume Resistivity	ohm-cm	2.30 <sup>17</sup>		ASTM D257
<b>Results Below - polyimide film data only</b>				
UL Electrical RTI	°C	240		UL746B
UL Mechanical RTI	°C	200		UL746B
Flammability	UL-94	V-0		UL Test Method
Moisture Absorption, 100% RH	%	2.2		ASTM D570
Water Vapor Permeability	g/m <sup>2</sup> /day	8.4		ASTM E96
Hydroscopic Coefficient of Expansion	ppm/% RH	9		-



For more information on DuPont™ Kapton® polyimide films or other DuPont products, please visit our website.

[kapton.com](http://kapton.com)

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. It may be subject to revision as new knowledge and experience becomes available. This information is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. Since we cannot anticipate all variations in end-use and disposal conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102-5 and "DuPont Policy Regarding Medical Applications" H-50103-5.

DuPont™, the DuPont Oval Logo, and all products, unless otherwise noted, denoted with ™, ® or ® are trademarks, service marks or registered trademarks of affiliates of DuPont de Nemours, Inc. Copyright © 2020 DuPont de Nemours Inc. All rights reserved.

EI-10141 (3/20)